

# Santa Cecilia Dark

One of the first entries on the multifamily scene, Santa Cecilia White or White Rose is quarried in Brazil. It is classically elegant with rich hues of white/grey interspersed with flawless even grains of black & bordeaux.



GRANITE

## physical test results

		Imperial	Metric
Absorption by weight	ASTM C97	0.256%	0.256%
Density	ASTM C97	164.4 lb/ft <sup>3</sup>	2 633.44 kg/m <sup>3</sup>
Compressive strength	ASTM C170	34 027 Psi	234.61 MPa
Flexural strength	ASTM C880	2 495 Psi	14.9 MPa
Modulus of rupture	ASTM C99	1 937 Psi	13.36 MPa



*Superior*  
起日方昇

www.superiorsstone.com

Rm502, Xinao Rd, Jinhai St, Xiang'an District, Xiamen, China

Mobile: +86-13859904931

hoston@superior-surfaces.com

Natural stone products inherently lack uniformity & are subject to variation in aesthetics—color, shade, finish, etc. and performance—hardness, strength. When & where your stone is quarried will affect color. Check local building codes prior to specification & installation to verify that the product technical characteristics comply with required parameters. Final selection should be made from sample submittals. The existence & dimensions of bevel may vary from lot to lot. WARNING: This product can expose you to chemicals known to cause cancer, including crystalline silica (airborne particles of respirable size) in dust created if the product is dry cut/ground/polished or pulverized during fabrication/installation/removal. For more info go to P65warnings.ca.gov