



广微测
Gmicro Testing



201819000883



中国认可
国际互认
检测
TESTING
CNAS L1747



推荐实验室

广东省微生物分析检测中心

GUANGDONG DETECTION CENTER OF MICROBIOLOGY

分析检测报告

REPORT FOR ANALYSIS

报告编号

2024FM16088R01D

Report №.

样品名称

dolomite quartz

Name of Sample

委托单位

厦门旭日方升石业有限公司
XIAMEN SUPERIOR STONE CO., LTD.

Applicant

检测类型

委托检测
Entrustment Test

Test Type

单位地址: 广州市先烈中路 100 号大院 66 号楼

Address: Building 66, No. 100, Xianlie Middle Road, Guangzhou, China

邮政编码: 510070

Postcode:

电话号码: (020)87137666

Tel:

传真号码: (020)87137668

Fax:

网 址: www.gddcm.com

Website:





广微测
Gmicro Testing

广东省微生物分析检测中心

GUANGDONG DETECTION CENTER OF MICROBIOLOGY

分析检测报告

REPORT FOR ANALYSIS



报告编号 (Report No.) 2024FM16088R01D 校验码 (Verification Code) : SBQ4QQFV

样品名称 Name of Sample	dolomite quartz	检测类型 Test Type	委托检测 Entrustment Test
委托单位 Applicant	厦门旭日方升石业有限公司 XIAMEN SUPERIOR STONE CO., LTD.	地址 Address	福建省厦门市翔安区金海街道新澳路 500 号 502 室 Room 502, No.500, Xinao Road, Xiang'an District, Xiamen, China.
样品来源 Sample Source	委托方送检 Submitted for Testing by the Applicant	样品数量 Sample Quantity	12 块 12 pcs
样品规格和批号 Spec and Lot No of Sample	—	样品状态和特性 State and Characteristic	块状 Nubby
接样日期 Sample Received Date	2024-08-26	验讫日期 Completion Date	2024-09-05
检测项目 Item Tested	抗菌性能 Antibacterial properties		
检测依据和方法 Test Standard and Method	JC/T 897-2014		
检测结论 Test Conclusion	<p>经检验, 该样品对大肠杆菌 (AS 1.90) 和金黄色葡萄球菌 (AS 1.89) 的抗菌率分别为 6.25%、61.11%。</p> <p>The results showed that the antibacterial rates of <i>Escherichia coli</i> (AS 1.90) and <i>Staphylococcus aureus</i> (AS 1.89) were 6.25% and 61.11%, respectively.</p>		
备注 Remarks	<p>签发日期: 2024-09-05 Issue Date</p> <p>(机构盖章 Official Seal)</p>		



制表:
Editor

李亿峰

审核:
Verifier

孙延平

批准:
Approver

林保



广东省微生物分析检测中心

GUANGDONG DETECTION CENTER OF MICROBIOLOGY

分析检测结果

ANALYSIS AND TEST RESULT

报告编号 (Report No.) : 2024FM16088R01D

测试微生物 The tested organism	接种菌液浓度 Concentration of inoculum (cfu/mL)	空白对照样品“0” 接触菌落总数 Colonies of contact blank control samples at “0” time (cfu/ piece)	空白对照样品培养 24h 后菌落总数 Colonies of contact blank control samples at “24” time (cfu/ piece)	抗菌陶瓷试样培养 24h 后菌落总数 Colonies of contact antibacterial ceramic sample at “24” time (cfu/ piece)	抗菌率 Antibacterial rate (%)
大肠杆菌 (<i>Escherichia coli</i>) AS1.90	2.9×10 ⁴	8.4×10 ³	6.4×10 ⁶	6.0×10 ⁶	6.25
金黄色葡萄球菌 (<i>Staphylococcus aureus</i>) AS1.89	2.9×10 ⁴	8.2×10 ³	3.6×10 ⁶	1.4×10 ⁶	61.11

(以下空白 Blank Below)





报告编号 (Report No.) : 2024FM16088R01D

注意事项 Notice Items

1. 检测报告无本机构检验检测专用章、骑缝章无效。

The test report is invalid without the special stamp of testing and paging seal.

2. 检测报告无制表、审核、批准人签字无效。

The test report is invalid without the signatures of the editor, the verifier and the approver.

3. 检测报告涂改增删无效。

The test report is invalid if being supplemented, deleted or altered.

4. 未经本机构书面同意, 不得部分复制 (全部复制除外) 检测报告。

Without prior written permission, the test report cannot be reproduced, except in full.

5. 除非另有说明, 检测报告仅对来样负责。

Unless otherwise stated, the results shown in this test report refer only to the sample(s) tested.

6. 对检测报告有异议的, 应于收到报告之日起十五日内提出, 逾期不予受理。

Any dispute of the test report must be raised to the testing institution within 15 days after the test report is received, exceeding which the dispute will not be accepted.

7. 对送检样品, 样品信息由委托方提供, 本机构不对其真实性负责。

For the sample(s) submitted for testing, the sample information is provided by the applicant, and this testing institution is not responsible for its authenticity.

